

Serge 600 - linen | sand (008003)

Technical info

FRONT



BACK



Widths		250 cm 270 cm
Composition		Fibreglass 42% - PVC 58%
Openness factor	NBN EN 410	5.00%
Weight	NF EN 12127	525.00 g/m ²
Thickness	ISO 5084	0.74 mm
Density	ISO 7211/2	WARP 18.00 yarn/cm WEFT 14.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Color fastness to artificial weathering	ISO 105 B04	>7
Air permeability	ISO 9237	580.00 l/m ² /s
Roll length		50 m / 30 m for all widths > 270 cm
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B1
└ UK	BS 5867	C
└ USA	NFPA 701	FR

Serge 600 - linen sand (008003)		Technical info	
Tear strength	ISO 4674-1 methode 2		
↳ Original		WARP 8.50 daN	WEFT 7.50 daN
↳ After climatic chamber -30°C		WARP 7.80 daN	WEFT 7.50 daN
↳ After climatic chamber +70°C		WARP 8.20 daN	WEFT 7.20 daN
Elongation up to break	ISO 1421		
↳ Original		WARP 3.10 %	WEFT 2.75 %
↳ After color fastness to artificial light		WARP 4.00 %	WEFT 2.90 %
↳ After colour fastness to artificial weathering		WARP 3.50 %	WEFT 2.80 %
↳ After climatic chamber -30°C		WARP 3.00 %	WEFT 2.50 %
↳ After climatic chamber +70°C		WARP 2.85 %	WEFT 2.50 %
Breaking strength	ISO 1421		
↳ Original		WARP 260.00 daN/5cm	WEFT 225.00 daN/5cm
↳ After color fastness to artificial light		WARP 240.00 daN/5cm	WEFT 220.00 daN/5cm
↳ After colour fastness to artificial weathering		WARP 240.00 daN/5cm	WEFT 225.00 daN/5cm
↳ After climatic chamber -30°C		WARP 225.00 daN/5cm	WEFT 200.00 daN/5cm
↳ After climatic chamber +70°C		WARP 180.00 daN/5cm	WEFT 185.00 daN/5cm

Front - Interior	Serge 600 - linen sand (008003)
-------------------------	-----------------------------------

Visual properties	
Tv = Visual light transmittance	4.90%
Tuv = UV transmittance	2.00%

Solar energetic properties	
As = Solar absorptance	49.30%
Rs = Solar reflectance	43.90%
Ts = Solar transmittance	6.80%

Fabric + glazing: G-factor				
	G	Te	Qi	SC
Glazing A	0.46	0.06	0.41	0.55
Glazing B	0.47	0.05	0.42	0.62
Glazing C	0.43	0.04	0.39	0.72
Glazing D	0.27	0.02	0.25	0.84

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort		
Normal solar transmittance	Class 4	Very good effect
Glare control	Class 2	Moderate effect
Privacy night	Class 2	Moderate effect
Visual contact with the outside	Class 2	Moderate effect
Daylight utilisation	Class 1	Little effect

Thermal comfort G-factor = Total solar energy transmittance			
Glazing A	Glazing B	Glazing C	Glazing D
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor			
Glazing A	Glazing B	Glazing C	Glazing D
Class 0	Class 0	Class 0	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

Back - Interior	Serge 600 - linen sand (008003)
------------------------	-----------------------------------

Visual properties	
Tv = Visual light transmittance	4.90%
Tuv = UV transmittance	2.00%

Solar energetic properties	
As = Solar absorptance	44.90%
Rs = Solar reflectance	48.30%
Ts = Solar transmittance	6.80%

Fabric + glazing: G-factor				
	G	Te	Qi	SC
Glazing A	0.44	0.06	0.38	0.52
Glazing B	0.45	0.05	0.40	0.59
Glazing C	0.41	0.04	0.37	0.70
Glazing D	0.27	0.02	0.24	0.83

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort		
Normal solar transmittance	Class 4	Very good effect
Glare control	Class 2	Moderate effect
Privacy night	Class 2	Moderate effect
Visual contact with the outside	Class 2	Moderate effect
Daylight utilisation	Class 1	Little effect

Thermal comfort G-factor = Total solar energy transmittance			
Glazing A	Glazing B	Glazing C	Glazing D
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor			
Glazing A	Glazing B	Glazing C	Glazing D
Class 0	Class 0	Class 0	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

Front - Exterior

Serge 600 - linen | sand (008003)

Visual properties

Tv = Visual light transmittance	4.90%
Tuv = UV transmittance	2.00%

Solar energetic properties

As = Solar absorptance	49.30%
Rs = Solar reflectance	43.90%
Ts = Solar transmittance	6.80%

Fabric + glazing: G-factor

	G	Te	Qi	SC
Glazing A	0.17	0.06	0.11	0.20
Glazing B	0.13	0.05	0.08	0.18
Glazing C	0.09	0.04	0.05	0.15
Glazing D	0.07	0.02	0.05	0.22

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Thermal comfort G-factor = Total solar energy transmittance

Glazing A	Glazing B	Glazing C	Glazing D
Class 2	Class 3	Class 4	Class 4

Thermal comfort Qi-factor = Secondary heat transfer factor

Glazing A	Glazing B	Glazing C	Glazing D
Class 2	Class 3	Class 3	Class 3

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

Back - Exterior

Serge 600 - linen | sand (008003)

Visual properties

Tv = Visual light transmittance	4.90%
Tuv = UV transmittance	2.00%

Solar energetic properties

As = Solar absorptance	44.90%
Rs = Solar reflectance	48.30%
Ts = Solar transmittance	6.80%

Fabric + glazing: G-factor

	G	Te	Qi	SC
Glazing A	0.16	0.06	0.10	0.18
Glazing B	0.13	0.05	0.08	0.17
Glazing C	0.08	0.04	0.05	0.14
Glazing D	0.07	0.02	0.05	0.21

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Thermal comfort G-factor = Total solar energy transmittance

Glazing A	Glazing B	Glazing C	Glazing D
Class 2	Class 3	Class 4	Class 4

Thermal comfort Qi-factor = Secondary heat transfer factor

Glazing A	Glazing B	Glazing C	Glazing D
Class 3	Class 3	Class 3	Class 3

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect