


**Serge 600 - white | white-pearl grey**  
(002061)

Technical info

FRONT



BACK



<b>Widths</b>		250 cm   270 cm   320 cm
<b>Composition</b>		Fibreglass 42% - PVC 58%
<b>Openness factor</b>	NBN EN 410	5.00%
<b>Weight</b>	NF EN 12127	525.00 g/m <sup>2</sup>
<b>Thickness</b>	ISO 5084	0.74 mm
<b>Density</b>	ISO 7211/2	WARP 18.00 yarn/cm      WEFT 14.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7
<b>Color fastness to artificial weathering</b>	ISO 105 B04	>7
<b>Air permeability</b>	ISO 9237	580.00 l/m <sup>2</sup> /s
<b>Roll length</b>		50 m / 30 m for all widths > 270 cm
<b>Cleaning</b>		With soapy water
<b>Confection</b>		By heat, high frequency or ultrasonic welding
<b>Fire classification</b>		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B1
└ UK	BS 5867	C
└ USA	NFPA 701	FR

**Serge 600 - white | white-pearl grey**  
(002061)

Technical info

<b>Tear strength</b>	ISO 4674-1 methode 2		
↳ Original		WARP 8.50 daN	WEFT 7.50 daN
↳ After climatic chamber -30°C		WARP 7.80 daN	WEFT 7.50 daN
↳ After climatic chamber +70°C		WARP 8.20 daN	WEFT 7.20 daN
<b>Elongation up to break</b>	ISO 1421		
↳ Original		WARP 3.10 %	WEFT 2.75 %
↳ After color fastness to artificial light		WARP 4.00 %	WEFT 2.90 %
↳ After colour fastness to artificial weathering		WARP 3.50 %	WEFT 2.80 %
↳ After climatic chamber -30°C		WARP 3.00 %	WEFT 2.50 %
↳ After climatic chamber +70°C		WARP 2.85 %	WEFT 2.50 %
<b>Breaking strength</b>	ISO 1421		
↳ Original		WARP 260.00 daN/5cm	WEFT 225.00 daN/5cm
↳ After color fastness to artificial light		WARP 240.00 daN/5cm	WEFT 220.00 daN/5cm
↳ After colour fastness to artificial weathering		WARP 240.00 daN/5cm	WEFT 225.00 daN/5cm
↳ After climatic chamber -30°C		WARP 225.00 daN/5cm	WEFT 200.00 daN/5cm
↳ After climatic chamber +70°C		WARP 180.00 daN/5cm	WEFT 185.00 daN/5cm

**Front - Interior** Serge 600 - white | white-pearl grey (002061)

Visual properties	
<b>Tv = Visual light transmittance</b>	11.60%
<b>Tuv = UV transmittance</b>	3.40%

Solar energetic properties	
<b>As = Solar absorptance</b>	27.70%
<b>Rs = Solar reflectance</b>	59.80%
<b>Ts = Solar transmittance</b>	12.40%

Fabric + glazing: G-factor				
	<b>G</b>	<b>Te</b>	<b>Qi</b>	<b>SC</b>
<b>Glazing A</b>	0.38	0.11	0.27	0.45
<b>Glazing B</b>	0.40	0.09	0.30	0.52
<b>Glazing C</b>	0.38	0.07	0.30	0.64
<b>Glazing D</b>	0.26	0.04	0.21	0.80

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort		
<b>Normal solar transmittance</b>	Class 4	Very good effect
<b>Glare control</b>	Class 1	Little effect
<b>Privacy night</b>	Class 2	Moderate effect
<b>Visual contact with the outside</b>	Class 1	Little effect
<b>Daylight utilisation</b>	Class 1	Little effect

Thermal comfort G-factor = Total solar energy transmittance			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 1	Class 0	Class 0	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

**Back - Interior** Serge 600 - white | white-pearl grey (002061)

Visual properties	
<b>Tv = Visual light transmittance</b>	11.60%
<b>Tuv = UV transmittance</b>	3.40%

Solar energetic properties	
<b>As = Solar absorptance</b>	23.40%
<b>Rs = Solar reflectance</b>	64.20%
<b>Ts = Solar transmittance</b>	12.40%

Fabric + glazing: G-factor				
	<b>G</b>	<b>Te</b>	<b>Qi</b>	<b>SC</b>
<b>Glazing A</b>	0.35	0.11	0.25	0.42
<b>Glazing B</b>	0.37	0.09	0.28	0.49
<b>Glazing C</b>	0.36	0.07	0.29	0.61
<b>Glazing D</b>	0.25	0.04	0.21	0.79

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort		
<b>Normal solar transmittance</b>	Class 4	Very good effect
<b>Glare control</b>	Class 1	Little effect
<b>Privacy night</b>	Class 2	Moderate effect
<b>Visual contact with the outside</b>	Class 1	Little effect
<b>Daylight utilisation</b>	Class 1	Little effect

Thermal comfort G-factor = Total solar energy transmittance			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 1	Class 1	Class 1	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

<b>Front - Exterior</b>	Serge 600 - white   white-pearl grey (002061)
-------------------------	---

<b>Visual properties</b>	
<b>Tv = Visual light transmittance</b>	11.60%
<b>Tuv = UV transmittance</b>	3.40%

<b>Solar energetic properties</b>	
<b>As = Solar absorptance</b>	27.70%
<b>Rs = Solar reflectance</b>	59.80%
<b>Ts = Solar transmittance</b>	12.40%

<b>Fabric + glazing: G-factor</b>				
	<b>G</b>	<b>Te</b>	<b>Qi</b>	<b>SC</b>
<b>Glazing A</b>	0.17	0.11	0.06	0.20
<b>Glazing B</b>	0.15	0.09	0.05	0.19
<b>Glazing C</b>	0.11	0.07	0.03	0.18
<b>Glazing D</b>	0.08	0.04	0.04	0.24

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

<b>Thermal comfort G-factor = Total solar energy transmittance</b>			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 2	Class 3	Class 3	Class 4

<b>Thermal comfort Qi-factor = Secondary heat transfer factor</b>			
<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 3	Class 3	Class 3	Class 3

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

**Back - Exterior**

Serge 600 - white | white-pearl grey (002061)

**Visual properties**

<b>Tv = Visual light transmittance</b>	11.60%
<b>Tuv = UV transmittance</b>	3.40%

**Solar energetic properties**

<b>As = Solar absorptance</b>	23.40%
<b>Rs = Solar reflectance</b>	64.20%
<b>Ts = Solar transmittance</b>	12.40%

**Fabric + glazing: G-factor**

	<b>G</b>	<b>Te</b>	<b>Qi</b>	<b>SC</b>
<b>Glazing A</b>	0.16	0.11	0.05	0.19
<b>Glazing B</b>	0.14	0.09	0.05	0.18
<b>Glazing C</b>	0.10	0.07	0.03	0.17
<b>Glazing D</b>	0.07	0.04	0.03	0.23

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

**Thermal comfort G-factor = Total solar energy transmittance**

<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 2	Class 3	Class 3	Class 4

**Thermal comfort Qi-factor = Secondary heat transfer factor**

<b>Glazing A</b>	<b>Glazing B</b>	<b>Glazing C</b>	<b>Glazing D</b>
Class 3	Class 3	Class 4	Class 3

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect